



# For Meeting Your DEMANDING APPLICATIONS

## SPECIFICATION SHEET

**FIBREX Plus** is manufactured with increased mechanical properties compared to FIBREX Standard. This high-performance panel is suggested to meet your most critical and demanding applications.

FIBREX PLUS				
St. Stephen, NB				
Thickness Range	(in./mm)	0.079 - 0.114" / 2mm - 2.9mm	0.118 - 0.154" / 3.0mm - 3.9mm	0.157 - 0.217" / 4.0mm - 5.5mm
Average MOR	(psi)	6,800	6,800	6,800
Average Internal Bond	(psi)	230	230	230
Un-sanded Thickness Tolerance	(in.)	+/- .010	+/- .010	+/- .012
Sanded Thickness Tolerance	(in.)	+/- .005	+/- .005	+/- .006
Length	(in.)	+/- 1/8	+/- 1/8	+/- 1/8
Width	(in.)	+/- 1/16	+/- 1/16	+/- 1/16
Squareness	(in.)	+/- 5/32	+/- 5/32	+/- 5/32

- The above physical properties are based on target averages of individual production lots. Sampling for conformance to the above specifications must be done in accordance with the procedures described in the American National Standard for MDF. (ANSI A208.2 – 2016 section 6.2 Sampling for Acceptance)
- Complies with formaldehyde emission requirements for MDF in CPA-ECC-2011, ANSI 208.2-2016 and CCR 93120.2 (CARB Composite Wood ATCM Phase II).
- All panels are approved for interior, non-structural application.
- Contains 100% Recycled/Recovered wood content.

California Proposition 65 Requirement:

Warning: Drilling, sawing, sanding or machining wood products generates wood dust, a substance known to the State of California to cause cancer. Avoid inhaling wood dust or use a dust mask or other safeguards for personal protection.



renewables  
for a  
better life